

Technical information

Hard wax C13

Art. No. 400 364
400 366
400 368
402 058
409 671

HARO®

Quality Flooring

Uses	<ul style="list-style-type: none">- For the repair of minor and medium-severe damage on a flat surface or on an edge.- To be used on surfaces that are subject to medium-severe use.- For solid wood, veneer, foil, thermosetting, thermoplastic and plastic surfaces for interior use.- Recommended for indoor use.										
Characteristics	<ul style="list-style-type: none">- Mixture of mineral waxes, coloured with earth and oxide dyes.- Good adhesion properties.- Colour shades to be intermixed during melting.- Can be stripped off easily by means of the Specia Fillers Applicator, a chisel or the Metal Planer.										
Specifications	<table><tr><td>Softening point:</td><td>76°C (ISO 2207)</td></tr><tr><td>Dropping point:</td><td>81°C (DIN 51 801)</td></tr><tr><td>Mechanical stability:</td><td>good</td></tr><tr><td>Adhesion:</td><td>good adhesion to all plastics, soft and hard woods.</td></tr><tr><td>Shelf life:</td><td>unlimited</td></tr></table>	Softening point:	76°C (ISO 2207)	Dropping point:	81°C (DIN 51 801)	Mechanical stability:	good	Adhesion:	good adhesion to all plastics, soft and hard woods.	Shelf life:	unlimited
Softening point:	76°C (ISO 2207)										
Dropping point:	81°C (DIN 51 801)										
Mechanical stability:	good										
Adhesion:	good adhesion to all plastics, soft and hard woods.										
Shelf life:	unlimited										
Safety precautions	<ul style="list-style-type: none">- The product is not subject labelling in terms of the Council Directive Regulation 67/548/EEC article 23.- Keep out of reach of children.										

This technical information is for your guidance and is based on our most up to date knowledge. This is not an assurance of the properties of the described product with regard to the legal provisions of the Guarantee.

Hamberger Flooring GmbH & Co. KG

Postfach 10 03 53

D-83003 Rosenheim

www.haro.com

Phone +49 8031 700-0

Fax +49 8031 700-299

E-mail: mail@hamberger.de